CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24** **Date: 09/12/2019**

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 13-11-19

Customer ID : FF Chejja Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Chejja Concrete	M20	11/11/2019	09/12/2019	149.69 X 151.41 X 151.68	22663	**8.048**	538.7	23.8	23.2
2	FF Chejja Concrete	M20	11/11/2019	09/12/2019	150.28 X 150.54 X 150.88	22622	**8.078**	502.9	22.2	
3	FF Chejja Concrete	M20	11/11/2019	09/12/2019	151.16 X 149.36 X 151.00	22577	**8.394**	533.2	23.6	

AE
Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24**

Date: 18/11/2019

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 13-11-19

Customer ID : Tie Beam Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Tie Beam Concrete	M25	11/11/2019	18/11/2019	149.38 X 149.31 X 149.89	22304	**8.527**	530.2	23.8	22.7
2	Tie Beam Concrete	M25	11/11/2019	18/11/2019	150.33 X 149.55 X 151.22	22483	**8.104**	497.8	22.1	
3	Tie Beam Concrete	M25	11/11/2019	18/11/2019	150.45 X 151.77 X 151.04	22832	**8.242**	505.0	22.1	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24**

Date: 18/11/2019

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 13-11-19

Customer ID : Tie Beam Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Tie Beam Concrete	M25	11/11/2019	18/11/2019	149.36 X 149.36 X 149.79	22309	**8.527**	514.2	23.0	22.6
2	Tie Beam Concrete	M25	11/11/2019	18/11/2019	151.16 X 150.63 X 150.66	22769	**8.104**	502.8	22.1	
3	Tie Beam Concrete	M25	11/11/2019	18/11/2019	150.32 X 151.73 X 150.49	22807	**8.242**	518.6	22.7	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

Sig.
Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24** **Date: 09/12/2019**

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 13-11-19

Customer ID : Tie Beam Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Tie Beam Concrete	M25	11/11/2019	09/12/2019	151.74 X 149.54 X 151.16	22692	**8.885**	619.9	27.3	27.5
2	Tie Beam Concrete	M25	11/11/2019	09/12/2019	149.52 X 150.81 X 149.09	22549	**8.679**	590.1	26.2	
3	Tie Beam Concrete	M25	11/11/2019	09/12/2019	150.71 X 151.85 X 150.66	22886	**8.429**	662.9	29.0	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24** **Date: 18/11/2019**

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 13-11-19

Customer ID : Tie Beam Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Tie Beam Concrete	M25	11/11/2019	18/11/2019	150.06 X 151.33 X 151.22	22708	**8.527**	523.0	23.0	22.8
2	Tie Beam Concrete	M25	11/11/2019	18/11/2019	149.63 X 151.44 X 151.25	22661	**8.104**	521.0	23.0	
3	Tie Beam Concrete	M25	11/11/2019	18/11/2019	149.28 X 151.12 X 149.92	22559	**8.242**	503.2	22.3	

AE
Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Sig.....
Date.....

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 09/12/2019

Lab ID	:	**CP-2020-02-07-24**
Project Name	:	Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.
Agency	:	Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.
Customer's Reference	:	EE(Project)YNKZone/WO/114/2017-18
Date of Receipt	:	13-11-19
Customer ID	:	Tie Beam Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	09/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Tie Beam Concrete	M25	11/11/2019	09/12/2019	150.52 X 149.45 X 150.06	22495	**8.885**	628.9	28.0	27.7
2	Tie Beam Concrete	M25	11/11/2019	09/12/2019	149.99 X 150.05 X 149.36	22507	**8.679**	604.4	26.9	
3	Tie Beam Concrete	M25	11/11/2019	09/12/2019	149.25 X 151.47 X 150.91	22608	**8.429**	638.1	28.2	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig. Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-55

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 18/11/2019

Lab ID	:	**CP-2020-02-07-24**
Project Name	:	Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.
Agency	:	Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.
Customer's Reference	:	EE(Project)YNKZone/WO/114/2017-18
Date of Receipt	:	13-11-19
Customer ID	:	Tie Beam Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	18/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Tie Beam Concrete	M25	11/11/2019	18/11/2019	150.83 X 151.78 X 151.54	22893	**8.527**	532.2	23.2	22.7
2	Tie Beam Concrete	M25	11/11/2019	18/11/2019	150.26 X 149.80 X 150.59	22509	**8.104**	517.3	23.0	
3	Tie Beam Concrete	M25	11/11/2019	18/11/2019	151.58 X 151.20 X 150.61	22919	**8.242**	504.4	22.0	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig. Date.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24**

Date: 29/11/2019

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 25-11-19

Customer ID : FF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Column Concrete	M25	22/11/2019	29/11/2019	150.03 X 150.22 X 151.41	22538	**8.527**	520.3	23.1	22.7
2	FF Column Concrete	M25	22/11/2019	29/11/2019	150.36 X 150.71 X 149.53	22661	**8.104**	514.5	22.7	
3	FF Column Concrete	M25	22/11/2019	29/11/2019	149.89 X 150.82 X 150.65	22606	**8.242**	502.5	22.2	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig. Date

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24** **Date: 20/12/2019**

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 25-11-19

Customer ID : FF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Column Concrete	M25	22/11/2019	20/12/2019	151.57 X 151.13 X 151.49	22906	**8.885**	618.5	27.0	27.4
2	FF Column Concrete	M25	22/11/2019	20/12/2019	151.46 X 151.99 X 149.88	23021	**8.679**	616.6	26.8	
3	FF Column Concrete	M25	22/11/2019	20/12/2019	150.87 X 150.04 X 151.41	22637	**8.429**	641.6	28.3	

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig. Date.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24** **Date: 29/11/2019**

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 25-11-19

Customer ID : FF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 29/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Column Concrete	M25	22/11/2019	29/11/2019	150.38 X 151.49 X 150.62	22782	**8.527**	538.0	23.6	22.9
2	FF Column Concrete	M25	22/11/2019	29/11/2019	149.61 X 150.72 X 150.40	22549	**8.104**	517.2	22.9	
3	FF Column Concrete	M25	22/11/2019	29/11/2019	149.57 X 150.43 X 151.78	22499	**8.242**	499.9	22.2	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

Sig.
Date.

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-02-07-24** **Date: 20/12/2019**

Project Name : Construction of Indoor Stadium with all Amenities at Sahakarnagara in Ward No:08 Kodigehalli, Kodigehalli Sub Division.

Agency : Sri.Abbu Samabasiva Reddy, #1-B-3, Sree Arcade Layout, 4th Block, DB Sandra, Vidyaranyapura, Bangalore-560097.

Customer's Reference : EE(Project)YNKZone/WO/114/2017-18

Date of Receipt : 25-11-19

Customer ID : FF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Column Concrete	M25	22/11/2019	20/12/2019	151.41 X 150.02 X 149.04	22714	**8.885**	632.1	27.8	27.9
2	FF Column Concrete	M25	22/11/2019	20/12/2019	150.08 X 151.87 X 151.73	22792	**8.679**	609.9	26.8	
3	FF Column Concrete	M25	22/11/2019	20/12/2019	150.67 X 150.42 X 151.64	22663	**8.429**	657.0	29.0	

Asst. Executive Engineer
Project Division
Yelahanka Zone
Bangalore

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****